

# SELEMIX® MATTING DATA - Solventborne

## 7-330 + 7-320 Cellulose Topcoats

Product	Matt	Semi-Matt	Semi-Gloss	Gloss
Matt Cellulose Binder 7-320	800	600	400	-
Gloss Cellulose Binder 7-330	-	200	400	750
Selemix NPXX Tinting Bases	200	200	200	250
<b>Gloss Level (60°)</b>	<b>10-20%</b>	<b>20-30%</b>	<b>40-50%</b>	<b>80-90%</b>
<b>Refer to TDS no:</b>	<b>515</b>	<b>515</b>	<b>515</b>	<b>516</b>

**Note:**

**All Gloss / Matt levels are measured at 60 degrees and are for dry film thicknesses of 50-60 microns**

**Gloss levels are approximate, and can vary depending on colour, application and drying conditions.**

## THIS PRODUCT IS FOR PROFESSIONAL USE ONLY

The information given in this sheet is for guidance only. Any person using the product without first making further enquiries as to the stability of the product for the intended purpose does so at his own risk and we can accept no liability for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of our experience and our policy of continuous product development. Drying times quoted are average times at 20°C. Film thickness, humidity and shop temperature can all affect drying times.

**FOR FURTHER INFORMATION PLEASE CONTACT:**

Selemix Customer Service and Sales Group  
 Needham Road  
 Stowmarket, Suffolk  
 IP14 2AD, England  
 Tel: 01449 771771