

SELEMIX[®] MATTING DATA

4-0090 + 4-0015 Clearcoats

Product	Matt	Semi-Matt	Semi-Gloss	Gloss
Matt Clearcoat 4-0015	100	95	85	-
Gloss Clearcoat 4-0090	-	5	15	100
Gloss Level (60°)	10-20%	20-30%	40-50%	80-90%
Refer to TDS no:	598	598	598	598

Note:

All Gloss / Matt levels are measured at 60 degrees and are for dry film thicknesses of 50-60 microns

Gloss levels are approximate, and can vary depending on colour, application and drying conditions.

THIS PRODUCT IS FOR PROFESSIONAL USE ONLY

The information given in this sheet is for guidance only. Any person using the product without first making further enquiries as to the stability of the product for the intended purpose does so at his own risk and we can accept no liability for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of our experience and our policy of continuous product development. Drying times quoted are average times at 20°C. Film thickness, humidity and shop temperature can all affect drying times.

FOR FURTHER INFORMATION PLEASE CONTACT:

Selemix Customer Service and Sales Group
Needham Road
Stowmarket, Suffolk
IP14 2AD, England
Tel: 01449 771771