

SELEMIX[®] MATTING DATA

8-552 + 8-553 2K POLYURETHANE TOPCOATS

Product	Matt	Semi-Matt	Semi-Gloss	Gloss
Matt PU Binder 8-553	60	36	30	-
Gloss PU Binder 8-552	-	24	30	60
<i>Selemix</i> WBXX Tinting Bases	40	40	40	40
Gloss Level (60°)	10-20%	40-50%	50-60%	>80%
Refer to TDS no:	610	610	610	608

Note:

All Gloss / Matt levels are measured at 60 degrees and are for dry film thicknesses of 40-50 microns for topcoats.

Gloss levels are approximate, and can vary depending on colour, application and drying conditions.

THIS PRODUCT IS FOR PROFESSIONAL USE ONLY

The information given in this sheet is for guidance only. Any person using the product without first making further enquiries as to the stability of the product for the intended purpose does so at his own risk and we can accept no liability for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of our experience and our policy of continuous product development. Drying times quoted are average times at 20°C. Film thickness, humidity and shop temperature can all affect drying times.

FOR FURTHER INFORMATION PLEASE CONTACT:

Selemix Customer Service and Sales Group
 Needham Road
 Stowmarket, Suffolk
 IP14 2AD, England
 Tel: 01449 771771