

SELEMIX® MATTING DATA - Solventborne

BINDER MATTING RATIOS – 7-410 + 7-412 Epoxy Topcoats

Product	Matt	Semi-Matt	Semi-Gloss	Gloss
Matt Epoxy Binder 7-412	800	600	500	-
Gloss Epoxy Binder 7-410	-	100	200	700
Selemix NPXX Tinting Bases	200	300	300	300
Gloss Level (60°)				
Air Dried over Metal	10-15%	40-50%	75-85%	>90%
Air Dried over Primer	15-20%	55-65%	75-85%	>90%
Oven Dried over Metal	20-25%	50-60%	80-90%	>90%
Oven Dried over Primer	25-30%	65-75%	80-90%	>90%
Refer to TDS no:	522	522	522	520

Note:

All Gloss / Matt levels are measured at 60 degrees and are for dry film thicknesses of 50-60 microns

Gloss levels are approximate, and can vary depending on colour, application and drying conditions.

THIS PRODUCT IS FOR PR

OFESSIONAL USE ONLY

The information given in this sheet is for guidance only. Any person using the product without first making further enquiries as to the stability of the product for the intended purpose does so at his own risk and we can accept no liability for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of our experience and our policy of continuous product development. Drying times quoted are average times at 20°C. Film thickness, humidity and shop temperature can all affect drying times.

FOR FURTHER INFORMATION PLEASE CONTACT:

Selemix Customer Service and Sales Group
 Needham Road
 Stowmarket, Suffolk
 IP14 2AD, England
 Tel: 01449 771771